



# ALUMINAS

## GROUND ALUMINAS 2

Type of product		Salox S50SG (ALO-G2-2)	Salox S15SGS1 (ALO-G32-2)	Salox S1FG (ALO-KN-4F)	Salox S1SG (ALO-KN-4S)
Al <sub>2</sub> O <sub>3</sub> *	%	min. 99.4	min. 99.4	min. 99.5	min. 99.5
Na <sub>2</sub> O <sub>total</sub>	%	max. 0.3	max. 0.3	max. 0.3	max. 0.3
Fe <sub>2</sub> O <sub>3</sub>	%	max. 0.03	max. 0.03	max. 0.04	max. 0.04
SiO <sub>2</sub>	%	max. 0.02	max. 0.02	max. 0.04	max. 0.04
CaO	%	max. 0.04	max. 0.04	max. 0.04	max. 0.04
Loss on ignition L.O.I.	%	max. 0.5	max. 0.5	max. 0.2	max. 0.2
Specific surface area BET	m <sup>2</sup> /g	12 - 30	6 - 12	max. 1.5	max. 1.5
Average particle size d <sub>50</sub>	µm	2 - 5	2 - 5	3 - 6	2 - 5
+ 45 µm (wet sieve)	%	max. 1	max. 1	max. 3	max. 0.1

\* By difference

Valid from: 01. 03. 2016

**SILKEM**  
**HUNGARY**

SILKEM Hungary Kft., H-8104 Várpalota, Fehérvári út 26., Hungary  
tel.: +36 88 544 100, fax: +36 88 371 889, e-mail: silkemhungary@silkem.hu  
cégjegyzékszám: 19-09-517537, adószám: 10647635-2-19