



# ALUMINIUM HYDROXIDES

page 1/1

## DRIED TYPES

Type of product		Dried types	
		ALOLT 01	ALOLT 1AF
Al(OH) <sub>3</sub> *	%	min. 99.5	min. 99.5
SiO <sub>2</sub>	%	max. 0.01	max. 0.01
Fe <sub>2</sub> O <sub>3</sub>	%	max. 0.02	max. 0.01
Na <sub>2</sub> O <sub>total</sub>	%	max. 0.2	max. 0.3
Moisture	%	max. 0.2	max. 0.2
Bulk density	kg/m <sup>3</sup>	max. 1400	max. 1300
Average particle size d <sub>50</sub>	µm	40 - 85	35 - 65
Whiteness	%	min. 80	min. 90

\* By difference

Valid from: 01. 01. 2020.

**SILKEM**  
**HUNGARY**

SILKEM Hungary Kft., H-8104 Várpalota, Fehérvári út 26., Hungary  
tel.: +36 88 544 100, fax: +36 88 371 889, e-mail: [silkemhungary@silkem.hu](mailto:silkemhungary@silkem.hu)  
cégjegyzékszám: 19-09-517537, adószám: 10647635-2-19